



General Properties of Pure Gum†

- Excellent physical properties.
- Excellent abrasion-resistance.
- Excellent low temperature resistance.
- Good resistance to most acids.

† Properties shown based on Rubber Manufacturers Association Sheet Rubber Handbook, second edition.



SPECIFICATIONS:

Tan pure gum rubber sheet:

Style GF490: 40 Duro hardness (Shore Durometer A)

Polymer: Isoprene rubber (natural)

Common Name: Natural Rubber Sheet

ISO/ASTM Designation: NR

Talc Free

Style	ASTM Specification (SI units)	Temp. Range	Durometer	Tensile Strength (psi)	Elongation (%)	Finish
GF490	D 2000 M4AA 417 A13 B13 G21	-40°F to +176°F	35 – 45	2500	600%	Plate

ORDERING INFORMATION:

Part Number	Gauge x Width (in)	Avg. Length (Linear ft/Roll)	Approx. lbs/Roll
GF490-02x36x67	1/16 x 36	67	68
GF490-04x36x50	1/8 x 36	50	102
GF490-04x36x67	1/8 x 36	67	137
GF490-06x36x50	3/16 x 36	50	153
GF490-06x36x67	3/16 x 36	67	205
GF490-08x36x36	1/4 x 36	36	147
GF490-08x36x50	1/4 x 36	50	204
GF490-12x36x36	3/8 x 36	36	221
GF490-16x36x18	1/2 x 36	18	147
GF490-24x36x18	3/4 x 36	18	221
GF490-32x36x18	1 x 36	18	294
GF490-01x48x67	1/32 x 48	67	46
GF490-02x48x67	1/16 x 48	67	91
GF490-04x48x36	1/8 x 48	36	98
GF490-04x48x50	1/8 x 48	50	136
GF490-06x48x36	3/16 x 48	36	147
GF490-06x48x50	3/16 x 48	50	204
GF490-08x48x18	1/4 x 48	18	98
GF490-08x48x50	1/4 x 48	50	273
GF490-12x48x50	3/8 x 48	50	409
GF490-16x48x25	1/2 x 48	25	273
GF490-24x48x25	3/4 x 48	25	409
GF490-32x48x25	1 x 48	25	545